

MANUFACTURER

ALLGEMEINE BAU - CHEMIE PHIL., INC.
 Address: 10th Floor Asian Star Building, 2404 Asean Drive,
 Filinvest Corporate City, Alabang, Muntinlupa City 1781 Philippines
 Tel: (+63 2) 8426891 ■ Fax: (+63 2) 8427146 ■ info@abc.ph ■ www.abc.ph

PRODUCT NAME


ABC SANITARY GRADE SILICONE SEALANT

PRODUCT DESCRIPTION

ABC SILICONE SEALANT SANITARY GRADE is a room temperature vulcanizing (RTV) acetic acid cure silicone sealant with outstanding adhesive strength. Its formulation with bio-tech system makes it resistant to mold and mildew. It is suitable for universal application for various glazing, caulking, grouting or sealing bathrooms and kitchens.

THE ABC SANITARY GRADE SILICONE SEALANT ADVANTAGE

- ✓ Low Modulus
- ✓ Non-slumping
- ✓ Waterproof
- ✓ Superior adhesion
- ✓ Air tight
- ✓ UV & Weather Resistant
- ✓ Permanently Elastic
- ✓ Anti-mold & mildew
- ✓ Anti-bacteria



COLOR

White

CLASSIFICATION STANDARD

- ✓ DIN 18545 (D) German Institute for Standardization
- ✓ TT-S-00-1543A (USA) American National Standards Institute
- ✓ ISO 8690 (UK) International Organization for Standardization
- ✓ BS 5889 (GB) Base Station Conformance Testing

TECHNICAL DATA

Uncured

Density at 23°C Consistency	DIN 53479-B	g/cm ³	1.03
	DIN 52454-profile B	non-slump	
Skin-forming time at 23°C 50% relative humidity		minutes	5 - 15
Vulcanization rate (curing) at 23°C 50% relative humidity		mm/d	1.0-2.0
Shrinkage during vulcanization	DIN 52451	%	3.5

The following data is intended as guideline and not for preparing specifications.

Cured

Tensile Strength	DIN 53504, rod S 3 A	N/mm ²	1.60
	DIN 52455, part 1	N/mm ²	0.70
Elongation at break	DIN 53504, rod S 3 A	N/mm ²	800
	DIN 52455, part 1	N/mm ²	200
Modulus of Elongation at 100% elongation	DIN 53504, rod S 3 A1	N/mm ²	0.30
	DIN 52455, part 1	N/mm ²	0.45
Tear resistance	ASTM D 624, rod B	N/mm ²	5.0
Hardness	DIN 53505, Shore A		18

Specimen measured after 4 weeks storage at 23°C/50% relative humidity.

SURFACE PREPARATION

The surface must be fully cured & structurally stable. Make sure the surface is dry, clean & free from contaminants such as dirt, dust, loose material, oils & chemicals.

TIP: For cleanest possible result and a perfectly straight line sealant application, especially in hard-to-reach places, use masking tape. Apply the tape covering both sides of the line to be sealed & then remove the tape before the sealant is dry.

APPLICATION GUIDE

1. Application

- a. Use a standard caulking gun to dispense the sealant.
Note: The use of a caulking gun ensures even distribution for a professional finish.


TIP: Hold the sealant gun at an angle of 45° while pulling the gun towards yourself. Find the right working speed to properly fill the necessary gaps.

- b. Ensure the sealant is in contact with both sides of joints and gaps. Use foam backer rods to establish good bonding at the sides and to control the depth of the sealant.

2. Finishing

Remove excess sealant and tool with flat knife. Depending on humidity & temperature, applied sealant is touch dry after 30 minutes. *Note: Protect from water exposure for at least 4 hours after application.*

APPLICATION AREAS



PACKAGING

300ml cartridge

STORAGE & SHELF LIFE

Store in a cool dry place. ABC Silicone Sealant Sanitary Grade will remain usable one year from date of manufacture.

WARRANTY

Due to variety of applications, different working methods and the various properties of bases, we cannot assume responsibility or liability with regard to the application of our products. Our guarantee and liability are restricted to the quality of our products at the time of acceptance of the customer of such products. In no case shall our liability extend beyond replacement of defective products, if any, found at the time of acceptance. For all deliveries and services, our General Sales Condition including warranties stipulated for each case are valid.

